

# Topological phase transition between the gap and the gapless superconductors

Yuriy Yerin,<sup>1</sup> Caterina Petrillo,<sup>1</sup> and A.A. Varlamov<sup>2</sup>

<sup>1</sup> *Dipartimento di Fisica e Geologia, Universit degli Studi di Perugia, Via Pascoli, 06123 Perugia, Italy*  
<sup>2</sup> *CNR-SPIN, c/o Dipartimento DICII, Universit "Tor Vergata", Viale del Politecnico 1, I-00133 Rome, Italy*  
(Dated: September 15, 2021)

It is demonstrated that the known for a long time transition between the gap and gapless superconducting states in the Abrikosov-Gor'kov theory of superconducting alloy with paramagnetic impurities is of the Lifshitz type, i.e. of the  $2\frac{1}{2}$  order phase transition. We prove that this phase transition has a topological nature and is characterized by the corresponding change of the topological invariant, namely the Euler characteristic. We study the stability of such a transition with respect to the spatial fluctuations of the magnetic impurities critical concentration  $n_s$  and show that the requirement for validity of its mean field description is unobtrusive:  $\nabla(\ln n_s) \ll \xi^{-1}$  (here  $\xi$  is the superconducting coherence length) Finally, we show that, similarly to the Lifshitz point, the  $2\frac{1}{2}$  order phase transition should be accompanied by the corresponding singularities, for instance, the superconducting thermoelectric effect has a giant peak exceeding the normal value of the Seebeck coefficient by the ratio of the Fermi energy and the superconducting gap. The concept of the experiment for the confirmation of  $2\frac{1}{2}$  order topological phase transition is proposed. Obtained theoretical results can be applied for the explanation of recent experiments with lightwave-driven gapless superconductivity, for the new interpretation disorder induced transition  $s_{\pm}$ - $s_{++}$  states via gapless phase in multi-band superconductors, and for the better understanding of gapless color superconductivity in quantum chromodynamics and the string theory.

PACS numbers:

*Introduction.* - In 1960, two seminal papers were published almost simultaneously, which gave rise to new directions in the research fields of superconductivity and fermiology [1, 3].

In the first paper, Abrikosov and Gor'kov, extending the BardeenCooperSchrieffer (BCS) theory to the case of a superconducting alloy containing paramagnetic impurities, demonstrated that the original BCS identification of the phenomenon of superconductivity with the presence of the gap in the quasiparticle spectrum is too limited, and, under some conditions, gapless superconductivity can exist. According to the Abrikosov-Gor'kov (AG) theory [1, 2], the transition between gap and gapless regimes was governed by the concentration of pair-breaking impurities and the properties of such superconducting system were studied in the mean-field approximation. Gapless superconductivity occurs in the very narrow interval of paramagnetic impurity concentrations  $0.912 n_c < n < n_c$ , where  $n_c$  is the concentration that completely suppresses the supercurrent flow. Later, it was recognized that the gapless regime in a superconductor can be induced by different mechanisms breaking the time-reversal symmetry: magnetic field, current [4], proximity effect [5] and the light [6]. However, the order of this transition, to the best of our knowledge, was never discussed.

In the second paper of I.M. Lifshitz [3] the notion of phase transition of fractional,  $2\frac{1}{2}$ , order was introduced. Also, it was pointed out that by varying some external parameter (pressure or concentration of the isovalent impurities) one can change the number of components of topological connectivity of the Fermi surface, which

is accompanied, according to the Ehrenfest terminology [7], by the  $2\frac{1}{2}$  order phase transition. Further studies of these, named today as Lifshitz's, transitions revealed that they are accompanied by singularities in various properties of the system undergoing them [8, 9].

The ideas proposed 60 years ago remain still valid in modern studies on the stability of current-biased superconducting wires (see [10] and references therein), transformations of the complex heavy fermion Fermi surfaces due to magnetic field effects [11, 12], etc. Moreover, the concept of a connection between the topological properties of the different materials exhibiting gapless states and the occurrence of the exotic Lifshitz transitions was recently discussed in literature based on very general topological arguments. Examples are given by Dirac and Weyl materials, and even more exotic systems (see the reviews [13, 14]).

In this Letter we aim at framing these concepts into a unified description and show that the known for a long time transition between gap and gapless superconducting states is the topological phase transition of the Lifshitz type, i.e. of the  $2\frac{1}{2}$  order. This will be proved by a very simple approach, in spirit of the fundamental paper [3], just analysing the properties of the free energy in a superconductor containing paramagnetic impurities.

However, while Lifshitz transitions are characterized by a change in the number of topologically connected components, it is the Euler-Poincare topological invariant that changes its value in the transition between the gap and the gapless phases.

Further, we study the requirements on the homogeneity of the paramagnetic impurities concentration, which

is necessary for the validity of the standard mean field approximation in the description of the “gap-gapless” transition used in [1], and we show the stability of the transition with respect to these fluctuations.

Finally, we argue that such a transition would be accompanied by the appearance of singularities in several properties, in particular an anomalous growth of the thermoelectric effect (see [15–18]) close to the critical concentration, which is valuable for the experimental verification of the proposed connection.

*Free energy and topological phase transition.* - We start from the expression for the free energy close to the transition between gapless and gap regimes at  $T = 0$  (see [4, 19]), that is

$$F_{s-n} = -\frac{N(0)\Delta^2}{2} \begin{cases} 1 - \frac{\pi}{2}\zeta + \frac{2}{3}\zeta^2, & \zeta \leq 1 \\ 1 - \zeta \arcsin \zeta^{-1} + \zeta^2 (1 - \sqrt{1 - \zeta^{-2}}) \\ -\frac{1}{3}\zeta^2 (1 - (1 - \zeta^{-2})^{3/2}), & \zeta > 1 \end{cases} \quad (1)$$

$\Delta$  is the order parameter ( $\Delta \in \mathbb{R}$ ) and  $N(0) = \frac{m\rho_F}{\pi^2\hbar^3}$  the density of states at the Fermi level. The parameter

$$\zeta = (\tau_s \Delta)^{-1}, \quad (2)$$

with  $\tau_s$  the electron spin-flip scattering time due to the presence of paramagnetic impurities, governs the phase transition between the gap and gapless states. Namely, when  $\zeta < 1$  the energy gap  $\Delta_g$  in the quasiparticle spectrum of a superconductor has a nonzero value, while for  $\zeta > 1$  the gapless state is realized and the energy gap remains identically equal to zero. At the same time the order parameter  $\Delta$  remains different from zero and the phenomenon of supercurrent flow occurs. The critical point  $\zeta = 1$  marks the gap and the gapless states. We remark that the authors of [1] were the first who pointed out at the importance of making a distinction between the order parameter  $\Delta$  and the energy gap  $\Delta_g$  existing in the quasiparticles spectrum. To elucidate what is the order of the topological phase transition, we first studied the behavior of the free energy (Eq. 1) and its derivatives over the parameter  $\zeta$  that drives the transition. It turns out that the free energy together with its first and second derivatives remain continuous function at the transition point  $\zeta = 1$ . However, the plot of the second derivative  $\partial^2 F_{s-n}/\partial\zeta^2$  unambiguously shows the kink at  $\zeta = 1$  (Fig. 1). Moreover, from the expression of the third derivative

$$\frac{\partial^3 F_{s-n}}{\partial\zeta^3} = N(0)\Delta^2 \begin{cases} 0, & \zeta \leq 1 \\ \frac{1}{\zeta^4\sqrt{\zeta^2-1}}, & \zeta > 1. \end{cases} \quad (3)$$

one can see the characteristic discontinuity with the square root singularity from the gapless side. The situation is completely analogous to the Lifshitz  $2\frac{1}{2}$  order




FIG. 1: The second derivative of Eq. (1) or specific heat capacity. The kink is clearly observed at  $\zeta = 1$ .

phase transitions in metals. The analogy is also confirmed by the quasiparticle density of states (DOS) dependence on the parameter  $\zeta$  driving transition [4]. Indeed, for the gap state ( $\zeta < 1, \Delta_g \neq 0$ )

$$N_s(\omega, \zeta < 1) = N(0) \begin{cases} 0, & \omega < \Delta_g \\ \zeta^{-\frac{2}{3}} (1 - \zeta^{\frac{2}{3}})^{-\frac{1}{4}} \sqrt{\frac{2}{3} \frac{\omega - \Delta_g}{\Delta}}, & \omega \geq \Delta_g, \end{cases} \quad (4)$$

while in the gapless state ( $\zeta > 1, \Delta_g = 0$ )

$$N_s(\omega, \zeta > 1) = N(0) \left[ (1 - \zeta^{-2})^{1/2} + \frac{3}{2} \zeta^{-4} (1 - \zeta^{-2})^{-5/2} \left( \frac{\omega}{\Delta} \right)^2 \right] \quad (5)$$

Eq. (5) shows that the density of states  $N_s(\omega)$  remains finite at  $\omega = 0$ , i.e.

$$N_s(0) = N(0) \frac{\sqrt{\zeta+1}}{\zeta} \sqrt{\zeta-1} \quad (6)$$

and has a typical cusp for  $2\frac{1}{2}$  order phase transition at  $\zeta = 1$ .

The discovered above in a formal way  $2\frac{1}{2}$  order phase transition unambiguously requires its topological interpretation. In the case of the Lifshitz transition in a normal metal the latter is trivial: the topological modification of the Fermi surface occurs when the chemical potential  $\mu$  reaches a certain critical value  $\mu_c$ , where the number of components of its topological connectivity changes. At this point the parameter  $z = \mu - \mu_c$  governing the transition passes through its zero value [9, 13, 14, 20, 21].




FIG. 2: Topological evolution of the DOS in the  $\omega$ - $\zeta$  space from the gap state with  $\zeta < 1$  (a) to the gapless state with  $\zeta \geq 1$  (b) combined with the similar topological behavior of the Fermi surface in the momentum space (c,d) for the Lifshitz transition (see detailed explanation in the text). Figure (a) with  $\zeta < 1$  is topologically equivalent to figure (c) with  $z < 0$ , while figure (b) with  $\zeta \geq 1$  is topologically equivalent to figure (d) with  $z > 0$ .

The topological interpretation of the found  $2\frac{1}{2}$  order phase transition can be given studying the modification of the DOS surface topology in the  $\omega$ - $\zeta$  space by exploiting its general expression [1, 2]

$$N(\omega, \zeta) = N(0) \zeta^{-1} \text{Im } u, \quad (7)$$

with  $u$  given by

$$\frac{\omega}{\Delta} = u \left( 1 - \frac{\zeta}{\sqrt{1-u^2}} \right) \quad (8)$$

Based on Eq. (7) one can find that the surfaces  $N(\omega, \zeta)$  are topologically dissimilar for  $\zeta < 1$  and  $\zeta \geq 1$  cases (see Fig. 2 a,b). The first case corresponds to the gap state with the narrowing space between two detached sheets of the DOS surfaces (Fig. 2 a). The second case characterizes the gapless state with the gradual degradation of the DOS curved surface to a plane when  $\zeta \rightarrow \infty$  (Fig. 2b).

It is interesting to note that at  $\zeta = 1$ , when the collapse of the energy gap occurs, the DOS surface acquires a topological feature known as the cuspidal edge [22]. The latter is the notion of the theory of catastrophes [23, 24]; it indicates on the occurrence of the catastrophe phenomenon in the  $\omega$ - $\zeta$  space over the gap-gapless phase transition, when two sheets of the DOS surfaces begin to collide with the increasing of  $\zeta$ .

Therefore, one can conclude that instead of parameter  $z$  that governs the Lifshitz transition and controls the corresponding transformation of an open Fermi surface into a closed one (Fig. 2c, d) with the emergence of the corresponding gap, the driving parameter for the topological modification under consideration is the value of  $\zeta$ .

Likewise the Lifshitz transitions are characterized by the change in the number of the topologically connected components, the identification of the topological phase transition between gap and gapless state can be conveniently done by introducing the topological invariant called Euler (or Euler-Poincaré) characteristic  $\chi$ . In general, the Euler characteristic can be calculated based on the Gauss-Bonnet theorem that establishes the connection between the Gaussian curvature of a surface and the value of  $\chi$  [25]. However, one can perform the polygonization of DOS surfaces and evaluate the Euler characteristic in a simple manner as  $\chi = V - E + F$  (where  $V$ ,  $E$ , and  $F$  are respectively the numbers of vertices (corners), edges and faces in the given polyhedron) [26] without the complicated calculation of a surface integral over the Gaussian curvature. This approach elucidates that during the topological transformation, which takes place at the point of gap-gapless Abrikosov-Gor'kov phase transition, the Euler characteristic changes from  $\chi = 2$  (gap state) to  $\chi = 1$  (gapless state).

*Smearing of the transition due to spacial fluctuations of the magnetic impurities concentration.* - In the case of the order parameter varying in space, Eq. (1) for the free energy can be generalized by adding heuristically the corresponding gradient term, like in the Ginzburg-Landau theory, that is

$$\begin{aligned} F &= -\frac{N(0)}{2} \left\{ a\Delta^2 + \frac{1}{4m} (\nabla\Delta)^2 \right\} \\ &= -\frac{N(0)}{2} \left\{ a\Delta^2 + \frac{1}{4m} \left( \frac{d\Delta}{d\zeta} \right)^2 \left( \frac{d\zeta}{dn_s} \right)^2 (\nabla n_s)^2 \right\}, \end{aligned} \quad (9)$$

where  $a = 1 - \frac{\pi}{2}\zeta + \frac{2}{3}\zeta^2$  and we recall that  $n_s$  is the concentration of magnetic impurities.

Here we already attributed the variation of the value of order parameter to the spacial inhomogeneity of the paramagnetic impurities distribution, elucidating the corresponding gradient in the last term of Eq. (9). One can neglect the impurities concentration fluctuations until the contribution of the “kinetic energy” remains small in comparison to the superconducting condensation energy.

Correspondingly, comparing the second term in Eq. (9) with the first one and using the expression determining the order parameter  $\Delta$  at  $T = 0$  [1, 4]

$$\ln \left( \frac{\Delta}{\Delta_0} \right) = \begin{cases} -\frac{\pi}{4}\zeta, & \zeta \leq 1 \\ -\text{arccosh } \zeta - \frac{1}{2} \left( \zeta \arcsin \zeta^{-1} - \sqrt{1-\zeta^{-2}} \right), & \zeta > 1, \end{cases} \quad (10)$$

we find (see [27]) that the fluctuations of the impurities concentration remain insignificant until

$$\frac{\nabla n_s}{n_s} \ll \frac{1}{\xi} \left( 1 - \frac{\pi}{2}\zeta + \frac{2}{3}\zeta^2 \right) \left( \frac{4}{\pi\zeta} - 1 \right) \quad (11)$$

This evaluation is valid close to the transition point  $\zeta = 1$  (indeed, the limit of superconductor without paramagnetic impurities  $\zeta \rightarrow 0$  does not make sense in such consideration), i.e.

$$\frac{d[\ln n_s(r)]}{dr} \ll \frac{1}{\xi}. \quad (12)$$




FIG. 3: Thermoelectric coefficient as a function of  $\zeta$  for different values of  $\tau_s\Delta_0$  for the given dimensionless inverse temperature  $\beta\Delta_0 = 50$  (up) and for different  $\beta\Delta_0$  for the fixed  $\tau_s\Delta_0 = 2.25$  (bottom). For both plots  $\tau_{tr}\Delta_0 = 1$ .

*Thermoelectric effect.* - It is well known that the Lifshitz transition in normal metals is accompanied by a giant asymmetric peak in the Seebeck coefficient [28–30]. Despite the opinion prevailing in the early period of the study of superconductivity concerning the vanishing of all conventional thermoelectric properties, today we know that a wide variety of interesting thermoelectric effects can exist in superconductors [31]. Among them is the quantization of the magnetic flux passing through the loop consisting of two different superconductors whose junctions are at different temperatures. As

demonstrated in [16] the correction to the integer number of flux quanta appears to depend on the temperature difference and thermoelectric coefficients of the superconductors in their normal state. Hence, one could expect the giant growth of this effect when one of the ring legs is close to the gap-gapless transition.

In order to demonstrate this we will calculate the corresponding quasiparticle contribution to the thermoelectric coefficient following the scheme proposed by Ambegaokar and Griffin to calculate the corresponding thermal conductivity (see Ref. 2). The thermoelectric coefficient  $\alpha$  relating the quasiparticle current to the temperature gradient, can be expressed in the form

$$\alpha = -\frac{eN(0)v_F^2}{4T^2} \int_{-\infty}^{+\infty} \frac{\omega d\omega}{\cosh^2\left(\frac{\beta\omega}{2}\right)} \times \frac{h(\omega, \Delta, \zeta)}{\text{Im} \left\{ \Omega(\omega, \Delta, \zeta) + \frac{i}{2\tau_{tr}} + \frac{i}{\tau_s} [1 - h(\omega, \Delta, \zeta)] \right\}}, \quad (13)$$

where  $\tau_{tr}$  is the transport collision time [1] that enters in the conductivity of a normal metal,  $v_F$  is the Fermi velocity. The functions  $h(\omega, \Delta, \zeta)$  and  $\Omega(\omega, \Delta, \zeta)$  are given by

$$\frac{\Omega(\omega, \Delta, \zeta)}{\Delta} = \sqrt{u^2 - 1} - i\zeta, \quad (14)$$

$$h(\omega, \Delta, \zeta) = \frac{1}{2} \left[ 1 + \frac{|u|^2 - 1}{|u^2 - 1|} \right], \quad (15)$$

where we recall that parameter  $u$  is defined by Eq. (8).

At temperatures close to zero (large values of  $\beta$ ) the main contribution to the integral in Eq. (13) comes from the low frequencies domain  $\omega \lesssim \beta^{-1}$ . Therefore, one can expand the parameter  $u$  and consequently the functions  $\Omega(\omega, |\Delta|, \zeta)$  and  $h(\omega, |\Delta|, \zeta)$  for small values of  $\omega$  and obtain the asymptotic behaviour of the thermoelectric coefficient close to the phase transition for both the gap and the gapless states. Approaching the transition from the gap side ( $\zeta \rightarrow 1-$ ) one finds (see Supplemental Material [27]) that the thermoelectric coefficient takes the form

$$\alpha = \frac{4\sqrt{2}\pi^2 T}{3e} \frac{\sigma_n \tau_s}{\Delta \tau_s + 2\tau_{tr}} \sqrt{1 - \zeta^{\frac{1}{3}}}, \quad (16)$$

where  $\sigma_n = \frac{2}{3}N(0)v_F^2 e^2 \tau_{tr}$ . Eq. (16) determines the magnitude of the Seebeck coefficient in the gap state. Recalling that the value of Seebeck coefficient in the normal metal is  $S_n = \frac{\pi^2 k_B}{3e} \frac{T}{E_F}$  one can find that  $S_g$  is giant with respect to the latter by the parameter  $E_F/\Delta$ :

$$S_g = \frac{\alpha}{\sigma_n} = \frac{2^{5/2}\tau_s}{\tau_s + 2\tau_{tr}} \left(1 - \zeta^{\frac{1}{3}}\right)^{\frac{1}{2}} \left(\frac{E_F}{\Delta}\right) S_n. \quad (17)$$

When performing the same procedure from the gapless side of the transition it can be disappointing to find  $\alpha \equiv$

0. Formally this is related to the oddness of the integrand function over  $\omega$  (see Ref. [27]) in this region. Yet, the obtained result does not mean that the thermoelectric coefficient here turns identically zero: in our expansions we did not retain terms of the order  $\omega/E_F$ , hence the thermoelectric effect from the right of transition point can be comparable to its normal background.

The results of the numerical calculations of the thermoelectric coefficient based on Eq. (13) are shown in Fig. 3. For the evaluation of  $\alpha$  we used the dependence of the order parameter modulus as a function of  $\zeta$  at zero temperature given by Eq. (10) and, for large values of  $\beta$  (i.e. in the vicinity of  $T = 0$ ), we assumed the temperature variation of  $\Delta$  to be very weak and approximated by Eq. (10).

There are several remarkable hallmarks of the found effect. First of all, the thermoelectric coefficient has a giant magnitude in the gap region. Second, the peak is asymmetric, and, third, the peak is shifted from the transition point into the gap domain ( $\zeta < 1$ ) when the temperature increases ( $\beta$  decreases). All these features are characteristic also for the Seebeck signal behaviour close to the  $2\frac{1}{2}$  phase transitions [8] and can be considered as the smoking gun for the experimental verification of the proposed phenomenon.

We should note that a similar strong enhancement of the thermoelectric coefficient by impurities was theoretically predicted in Ref. 32, 33. However, the authors of Ref. 32, 33 did not relate the giant thermoeffect to the manifestation of the  $2\frac{1}{2}$  phase transition. They specified that this phenomenon is caused by violation of the symmetry between electron-like and hole-like excitations due to formation of the subgap Andreev bound states in the vicinity of magnetic impurities [33].

From the experimental point of view the detection of such a topological phase transition can be performed by means of placing in magnetic field a ring, one half of which is a gap superconductor with the concentration of magnetic impurities close to the transition value and the other half is an arbitrary superconductor. In this case, provided superconducting contacts are kept at different but low temperatures, anomaly strong thermoelectric current is induced inside the ring and the measured magnetic flux should considerably deviate from the integer values of the magnetic flux quantum  $\Phi_0$  [17].

*Conclusions.* - We have demonstrated that the known for a long time transition between the gap and the gapless states of a superconducting alloy with paramagnetic impurities is the topological phase transition of the  $2\frac{1}{2}$  order. We found that the topological invariant in the form of the Euler characteristic changes from  $\chi = 0$  (gap state) to  $\chi = 1$  (gapless state) over the corresponding topological transformation. We have shown that the mean-field approximation used in the Abrikosov-Gor'kov theory [1] is very stable: fluctuations of the impurities concentration remain irrelevant in the logarithmic scale. Finally,

such a topological phase transition can be detected by the giant (by the parameter  $E_F/\Delta$  thermoelectric effect possessing the characteristic features which would clearly distinguish it from others. We have proposed an experiment for the detection of such an effect and the subsequent confirmation of the  $2\frac{1}{2}$  phase transition.

Our theoretical results may help to take a fresh look at recent experiments with lightwave-driven gapless superconductivity [6], for the new interpretation of the theoretically predicted disorder induced transition  $s_{\pm}$ - $s_{++}$  states via gapless phase in multi-band superconductors [34, 35] and can be useful for the understanding gapless color superconductivity in quantum chromodynamics and the string theory [36].

*Acknowledgements.* - A.A.V. is grateful to Yu. Galperin for valuable discussions. C.P. and Y.Y. acknowledge support by the CarESS project.

- 
- [1] A.A. Abrikosov, L.P.Gor'kov, *Contribution to the theory of superconducting alloys with paramagnetic impurities*, Sov. Phys. JETP **12**, 1243 (1961).
  - [2] Vinay Ambegaokar and Allan Griffin, *Theory of the Thermal Conductivity of Superconducting Alloys with Paramagnetic Impurities*, Phys. Rev. **137**, A1151 (1965).
  - [3] I.M. Lifshitz, *Anomalies of electron characteristics of a metal in the high pressure region*, Zh. Eksp. teor. Fiz. **38**, 1569 (1960).
  - [4] K. Maki, *Gapless Superconductivity*, Chapter 18, "Superconductivity" Edited by Parks, 1968.
  - [5] J. J. Hauser, *Gapless Superconductivity Induced by the Proximity Effect*, Phys. Rev. **164**, 558 (1967).
  - [6] X. Yang, C. Vaswani, C. Sundahl, M. Mootz, L. Luo, J. H. Kang, I. E. Perakis, C. B. Eom and J. Wang, *Lightwave-driven gapless superconductivity and forbidden quantum beats by terahertz symmetry breaking*, Nature Photonics **13**, 707 (2018).
  - [7] G. Jaeger, *The Ehrenfest Classification of Phase Transitions: Introduction and Evolution*, Arch. Hist. Exact Sci. **53**, 51 (1998).
  - [8] A.A. Varlamov, V. Egorov, and A. Pantsulaya, *Kinetic properties of metals near electronic topological transitions ( $2\frac{1}{2}$ -order transitions)*, Adv. Phys. **38**, 469 (1989).
  - [9] Y.M. Blanter, M.I. Kaganov, A.V. Pantsulaya, and A.A. Varlamov, *The theory of electronic topological transitions*, Phys. Rep. **245**, 159 (1994).
  - [10] Yu.N. Ovchinnikov, A.A. Varlamov, G.J. Kimmel, and A. Glatz, *Instabilities of the normal state in current-biased narrow superconducting strips*, Phys. Rev. B **101**, 014511 (2020).
  - [11] H. Pfau, R. Daou, S. Friedemann, S. Karbassi, S. Ghanadzadeh, R. Kuchler, S. Hamann, A. Steppke, D. Sun, M. König, A.P. Mackenzie, K. Kliemt, C. Krellner, and M. Brando, *Cascade of Magnetic-Field-Induced Lifshitz Transitions in the Ferromagnetic Kondo Lattice Material YbNi<sub>4</sub>P<sub>2</sub>*, Phys. Rev. Lett. **119**, 126402 (2017).
  - [12] A. Pourret, S.G. Sharapov, T.D. Matsuda, G. Knebel, G. Zwicky, and A.A. Varlamov, *Transport Spectroscopy of the Field Induced Cascade of Lifshitz Transitions*

- tions in  $\text{YbRh}_2\text{Si}_2$ , J. Phys. Soc. Jpn. **88**, 104702 (2019).
- [13] G.E. Volovik, *Exotic Lifshitz transitions in topological materials*, Phys.Usp. **61**, 89 (2018).
- [14] G.E. Volovik, *Topological Lifshitz transitions*, Low Temp. Phys. **43**, 47 (2017).
- [15] Yu.M. Galperin, V.L. Gurevich, V.I. Kozub, *Acoustoelectric and Thermoelectric Effects in Superconductors*, Sov. Phys. JETP Lett. **17**, 476 (1973).
- [16] Yu.M. Galperin, V.L. Gurevich, V.I. Kozub, *Nonlinear acoustic effects in superconductors*, Sov. Phys. JETP **65**, 1045 (1974).
- [17] N.V. Zavaritskii, *Thermoelectric phenomena in superconductors and thermomechanical circulation effect in a superfluid liquid* Pis'ma Zh. Eksp. Teor. Fiz. **20**, 223 (1974) [JETP Lett. **20**, 97 (1974)].
- [18] V.L. Ginzburg, G.F. Zharkov, A.A. Sobyenin, *Thermoelectric phenomena in superconductors and thermomechanical circulation effect in a superfluid liquid*
- [19] S.Skalski, O. Betbeder-Mattibet, and P.R. Weiss, *Properties of Superconducting Alloys Containing Paramagnetic Impurities* Phys. Rev. **136**, A1500, (1964).
- [20] Kuang Zhang and G.E. Volovik, *Lifshitz transitions via the type-II Dirac and type-II Weyl points*, Pis'ma ZhETF **105**, 504 (2017) [JETP Lett. **105**, 519 (2017)].
- [21] A. A. Varlamov, Y. M. Galperin, S. G. Sharapov, Yuriy Yerin, *Concise guide for electronic topological transitions*, Low Temperature Physics **47**, 672 (2021).
- [22] V.I. Arnold, Alexander Varchenko, S.M. Gusein-Zade, *Singularities of Differentiable Maps. Volume I: The Classification of Critical Points Caustics and Wave Fronts, (Monographs in mathematics ; Vol. 82)*, Birkhauser Boston Basel Stuttgart (1985).
- [23] V.I. Arnold, *Basic Concepts. In: Arnold V.I. (eds) Dynamical Systems V. Encyclopaedia of Mathematical Sciences, vol 5.*, Springer-Verlag Berlin Heidelberg (1994).
- [24] Kentaro Saji, Masaaki Umehara, Kotaro Yamada, *The geometry of fronts*, Annals of Mathematics **169**, 491 (2009).
- [25] Manfredo Perdigao do Carmo, *Differential geometry of curves and surfaces*. Upper Saddle River, N.J.: Prentice-Hall (1976)
- [26] E.H. Spanier, "Algebraic topology", McGraw-Hill pp. 156, (1966).
- [27] See the Supplemental Material for the detailed derivation of Eqs. (11), (12) and (16).
- [28] V.S. Egorov and A.N. Fedorov, *Thermopower of lithium-magnesium alloys at the 2 1/2 -order transition*, Zh. Eksp. Teor Phys. **85**, 1647 (1983) [Sov. Phys. JETP **58**, 959 (1983)].
- [29] V.G. Vaks, A.V. Trefilov, and S.V. Fomichev, *Singularities of resistivity and thermoelectric power of metals in phase transitions of order 2 1/2*, Th. Eksp. Teor. Fiz. **80**, 1613 (1981) [Sov.Phys. JETP **53**, 830 (1981)].
- [30] A.A. Varlamov and A.V. Pantsulaya, *Anomalous kinetic properties of metals near the Lifshitz topological transition*, Sov. Phys. JETP **62**, 1263 (1985).
- [31] D.J.Van Harlingen, *Thermoelectric effects in the superconducting state*, Physica B+C **109110**, 1710 (1982).
- [32] D. F. Digor and L. Z. Kon, *Thermoelectric effect in superconducting alloys*, Theoretical and Mathematical Physics **97**, 1137 (1993).
- [33] Mikhail S. Kalenkov, Andrei D. Zaikin, and Leonid S. Kuzmin, *Theory of a Large Thermoelectric Effect in Superconductors Doped with Magnetic Impurities*, Phys. Rev. Lett. **109**, 147004 (2012).
- [34] Victor Barzykin, *Magnetic-field-induced gapless state in multiband superconductors*, Phys. Rev. B **79**, 134517 (2009).
- [35] D. V. Efremov, M. M. Korshunov, O. V. Dolgov, A. A. Golubov, P. J. Hirschfeld, *Disorder-induced transition between s and s++ states in two-band superconductors*, Phys. Rev. B **84**, 180512(R) (2011).
- [36] Mark Alford, Jrgen Berges, and Krishna Rajagopal, *Gapless Color Superconductivity*, Phys. Rev. Lett. **84**, 598 (2000).

**SUPPLEMENTAL MATERIAL FOR  
"TOPOLOGICAL PHASE TRANSITION  
BETWEEN THE GAP AND THE GAPLESS  
SUPERCONDUCTORS"**

**SPACIAL FLUCTUATIONS OF THE MAGNETIC  
IMPURITIES CONCENTRATION**

Let us perform its evaluation, for simplicity, from the "gap side" of the phase transition. The first derivative in the "kinetic energy" term of Eq. (9) can be easily obtained by direct differentiation of Eq. (10) in the main paper:

$$\left(\frac{d\Delta}{d\zeta}\right) = -\frac{\pi}{4}\Delta. \quad (18)$$

What concerns the derivative  $d\zeta/dn_s$  its calculation is more delicate since  $\zeta = (\tau_s\Delta)^{-1}$ . The scattering lifetime  $\tau_s$  is determined by the integral over the solid angle  $\Omega$

$$\frac{1}{\tau_s} = \left[ N(0) \frac{S(S+1)}{(2S+1)^2} \int |f_+ - f_-|^2 d\Omega \right] n_s = An_s, \quad (19)$$

where  $n_s$  is the concentration of the magnetic impurities and  $f_+$  and  $f_-$  are the scattering amplitudes of an electron with a total angular momentum  $S + 1/2$  and  $S - 1/2$ .

Based on Eq. (19) and the fact that the order parameter  $\Delta$  depends on  $n_s$  we obtain

$$\frac{d\zeta}{dn_s} = \frac{A}{\Delta} - \frac{A}{\Delta^2} \frac{d\Delta}{dn_s} = \frac{A}{\Delta} - \frac{An_s}{\Delta^2} \frac{d\Delta}{d\zeta} \frac{d\zeta}{dn_s}. \quad (20)$$

Taking into account Eq. (18) one finds

$$\frac{d\zeta}{dn_s} = \frac{1}{n_s} \frac{\zeta}{1 - \frac{\pi\zeta}{4}}. \quad (21)$$

Relating the Cooper pair mass to the coherence length as  $\xi^2 = 1/(4ma)$  and returning to Eq. (9) in the main paper one finds that the kinetic energy term in the gap domain ( $\zeta < 1$ ) is expressed as

$$\frac{(\nabla\Delta)^2}{4m} = \frac{\pi^2\xi^2\Delta^2}{16} \frac{\zeta^2}{(1 - \frac{\pi\zeta}{4})^2} \left(\frac{\nabla n_s}{n_s}\right)^2. \quad (22)$$

## ASYMPTOTIC EXPRESSIONS FOR THE THERMOELECTRIC COEFFICIENT

In the vicinity of the zero temperature or for the large values of  $\beta$  the contribution to the Eq. (13) in the main paper gives the low order frequencies. Such a restriction allows to obtain several useful asymptotics for the thermoelectric coefficients from the gap and the gapless side of the phase transition. The starting point is the approximated expression for the parameter  $u$  in the case of the small  $\omega$ .

### Gap state

For the gap regime, where  $\zeta < 1$  we have

$$\frac{\omega - \Delta_g}{\Delta} = -\frac{3}{2}\zeta^{-\frac{2}{3}}\left(1 - \zeta^{\frac{2}{3}}\right)^{\frac{1}{2}}(u - u_0)^2, \quad (23)$$

where

$$\frac{\Delta_g}{\Delta} = \left(1 - \zeta^{\frac{2}{3}}\right)^{\frac{3}{2}}, \quad (24)$$

and

$$u_0 = \left(1 - \zeta^{\frac{2}{3}}\right)^{\frac{1}{2}}. \quad (25)$$

Substitution of Eqs. (24)-(25) into Eq. (23) yields an equation for  $u$  with the solution for  $\Delta_g = 0$ , i.e. when  $\zeta \rightarrow 1$

$$\begin{aligned} u &= \sqrt{1 - \zeta^{\frac{2}{3}}} \pm \frac{1}{3} \sqrt{\frac{6\zeta^{\frac{2}{3}} \left[ \left(1 - \zeta^{\frac{2}{3}}\right)^{\frac{3}{2}} - \frac{\omega}{\Delta} \right]}{\left(1 - \zeta^{\frac{2}{3}}\right)^{\frac{1}{2}}}} \\ &\approx \sqrt{2\left(1 - \zeta^{\frac{1}{3}}\right)} \pm \frac{1}{3} i \sqrt{\frac{6 \left[ \frac{\omega}{\Delta} - 2\sqrt{2}\left(1 - \zeta^{\frac{1}{3}}\right)^{\frac{3}{2}} \right]}{2^{\frac{1}{4}}\left(1 - \zeta^{\frac{1}{3}}\right)^{\frac{1}{4}}}} \end{aligned} \quad (26)$$

Based on Eqs. (26) for the parameter  $u$  one can write the expression for functions  $\Omega(\omega, \Delta, \zeta)$  and  $h(\omega, \Delta, \zeta)$  that are entered in Eq. (13) in the main paper for the thermoelectric coefficient in the main text. Introducing a new parameter  $z = \sqrt{1 - \zeta^{\frac{1}{3}}}$  near the the phase transition we have

$$\frac{\Omega(\omega, \Delta, \zeta)}{\Delta} = \sqrt{2z^2 + \frac{\sqrt{2}w}{3z} - 1 + i\frac{2}{3}2^{\frac{1}{4}}\sqrt{6zw} - i}, \quad (27)$$

and

$$h(\omega, \Delta, \zeta) = \frac{1}{2} \left[ 1 + \frac{2z^2 + \frac{\sqrt{2}w}{3z} - 1}{\sqrt{\left(2z^2 + \frac{\sqrt{2}w}{3z} - 1\right)^2 + \frac{8\sqrt{2}}{3}zw}} \right], \quad (28)$$

where  $w = \frac{\omega}{\Delta} - 2\sqrt{2}z^3$  and for the extraction of the square root of a complex number in Eq. (27) the well-known formula is applied

$$\sqrt{a + ib} = \pm \sqrt{\frac{\sqrt{a^2 + b^2} + a}{2}} \pm i \operatorname{sgn} b \sqrt{\frac{\sqrt{a^2 + b^2} - a}{2}}. \quad (29)$$

Using Eq. (27) and (28) one can expand in series for small  $\omega$  the part of the integrand in Eq. (13) in the main paper

$$\frac{h(\omega, \Delta, \zeta)}{\operatorname{Im} \left\{ \Omega(\omega, \Delta, \zeta) + \frac{i}{2\tau_{tr}} + \frac{i}{\tau_s} (1 - h(\omega, \Delta, \zeta)) \right\}} \approx \Upsilon_0(\zeta, \tau_{tr}, \tau_s) + \Upsilon_1(\zeta, \tau_{tr}, \tau_s) \frac{\omega}{\Delta} \quad (30)$$

where  $\Upsilon_0(\zeta, \tau_{tr}, \tau_s)$  and  $\Upsilon_1(\zeta, \tau_{tr}, \tau_s)$  are some function that we do not present explicitly due to their very cumbersome expressions. However, one can also perform the expansion in series of this function for  $z = 0$  or ( $\zeta = 1$ ) to simplify further analytical calculations

$$\Upsilon_1(\zeta, \tau_{tr}, \tau_s) \approx \frac{4\sqrt{2}}{3} \frac{\tau_s \tau_{tr}}{\tau_s + 2\tau_{tr}} z. \quad (31)$$

Therefore, combining Eqs. (30) and (31) finally we obtain asymptotic expression for the thermoelectric coefficient close to the phase transition from the gap side

$$\begin{aligned} \alpha &= \frac{8\sqrt{2}}{3} \frac{eN(0)Tv_F^2}{\Delta} \frac{\tau_s \tau_{tr}}{\tau_s + 2\tau_{tr}} z \int_{-\infty}^{+\infty} \frac{\omega^2 d\omega}{\cosh^2\left(\frac{\omega}{2T}\right)} = \\ &= \frac{4\sqrt{2}\pi^2}{9} \frac{eN(0)Tv_F^2}{\Delta} \frac{\tau_s \tau_{tr}}{\tau_s + 2\tau_{tr}} z = \\ &= \frac{4\sqrt{2}\pi^2}{9} \frac{eN(0)Tv_F^2}{\Delta} \frac{\tau_s \tau_{tr}}{\tau_s + 2\tau_{tr}} \sqrt{1 - \zeta^{\frac{1}{3}}} \end{aligned} \quad (32)$$

### Gapless state

In the case of the gapless regime, where  $\zeta > 1$  the expansion of  $u$  is given by

$$u = i\sqrt{\zeta^2 - 1} + \zeta^2(\zeta^2 - 1)^{-1} \frac{\omega}{\Delta} + \dots \quad (33)$$

This allows to obtain in the same way the expression for functions  $\Omega(\omega, \Delta, \zeta)$  and  $h(\omega, \Delta, \zeta)$  that are entered in Eq. (13) in the main paper for the thermoelectric coefficient in the main text. As in the previous case introducing a new parameter  $z = \sqrt{\zeta - 1}$  near the the phase transition one can write

$$\frac{\Omega(\omega, \Delta, \zeta)}{\Delta} = \sqrt{2z + \frac{1}{4} \frac{1}{z^2} \frac{\omega^2}{\Delta^2} - 1 + i \frac{\sqrt{2}}{\sqrt{z}} \frac{\omega}{\Delta} - i}, \quad (34)$$

and

$$h(\omega, \Delta, \zeta) = \frac{1}{2} \left[ 1 + \frac{2z + \frac{1}{4z^2} \frac{\omega^2}{\Delta^2} - 1}{\sqrt{\sqrt{(2z + \frac{1}{4z^2} \frac{\omega^2}{\Delta^2} - 1)^2 + \frac{2}{z} \frac{\omega^2}{\Delta^2}}} \right], \quad (35)$$

Based on Eq. (34) and (35) we expand in series for small  $\omega$  the part of the integrand in Eq. (13) in the main paper

$$\frac{h(\omega, \Delta, \zeta)}{\text{Im} \left\{ \Omega(\omega, \Delta, \zeta) + \frac{i}{2\tau_{tr}} + \frac{i}{\tau_s} (1 - h(\omega, |\psi|, \zeta)) \right\}} \approx \Theta_0(\zeta, \tau_{tr}, \tau_s) + \Theta_1(\zeta, \tau_{tr}, \tau_s) \frac{\omega^2}{\Delta^2}. \quad (36)$$

Due to long expressions for functions  $\Theta_0(\zeta, \tau_{tr}, \tau_s)$  and  $\Theta_1(\zeta, \tau_{tr}, \tau_s)$  we do not provide them in an explicit form. Nevertheless, since the expansion in series given by Eq. (36) contains only the even degree of  $\omega$  it is easy to understand that the integrand in Eq. (13) in the main paper is the odd function of  $\omega$  and, hence, the integral is equal to zero.